

# CONCRETE BOND - 108

## ASTM C881 COMPLIANT, HIGH MODULUS ADHESIVE

EPOXY BASED BONDING ADHESIVE

CONCRETE BOND-108

MASTER FORMAT

### DESCRIPTION

**CONCRETE BOND-108** is a 100% reactive, 2 component material designed as a moisture insensitive adhesive and binder for numerous application needs. This high modulus material is available in a low viscosity (LV), medium viscosity (MV) or GEL consistency. **CONCRETE BOND-108** provides normal working times when bonding concrete at temperatures above 40°F (4°C).

### WHERE TO USE

- Bonding old to new concrete, steel, ceramic or wood
- Anchoring bolts, dowels, and pins
- General adhesive needs
- Bonding concrete toppings
- GEL formulation are used for vertical and overhead bonding, anchoring, and repair
- Filling Cracks in concrete and masonry

### FEATURES/BENEFITS

- Moisture insensitive for bonding to dry or damp surfaces
- Bonds fresh concrete toppings to hardened concrete slabs
- Forms a tough, wear and chemical resistant coating for industrial floor slabs
- May be extended with sand or aggregate for thick applications and repairs
- Designed for use at temperatures of 40°F (4°C) and above
- Can contribute to LEED points

### SPECIFICATIONS/COMPLIANCES

**CONCRETE BOND-108 LV** complies with ASTM C881 Types I, II, IV, and V, Grade 1, Class B and C.

**CONCRETE BOND-108 MV** complies with ASTM C881 Types I, II, IV, and V, Grade 2, Class B and C.

**CONCRETE BOND-108 GEL** with ASTM C881 Types I,II,IV, and V, Grade 3, Class B and C.

**CONCRETE BOND-108 CARTRIDGE MV** complies with ASTM C881 Types I and IV, Grade 1, Class A, B, and C.

**CONCRETE BOND-108 CARTRIDGE GEL** complies with ASTM C881 Types I, II, IV, and V, Grade 3, Class B and C.

### SHELF LIFE

2years in original, unopened package.

### TECHNICAL INFORMATION

PROPERTY	CONCRETE BOND-108 LV	CONCRETE BOND-108 MV	CONCRETE BOND-108 GEL	CONCRETE BOND-108 CARTRIDGE MV	CONCRETE BOND-108 CARTRIDGE GEL
Gel Time	30 minutes	30 minutes	30 minutes	6 to 8 minutes	30 minutes
Working Time	90 minutes	90 minutes	90 minutes	10 to 20 minutes	90 minutes
Bond Strength	3,200 psi (22 MPa)	2,500 psi (17 MPa)	2,000 psi (14 MPa)	2,200 psi (15 MPa)	2,230 psi (15 MPa)
Water Absorption	0.15%	0.081%	0.4%	0.36%	0.31%
Compressive Modulus	397,600 psi (2,741 MPa)	321,664 psi (2,218 MPa)	265,000 psi (1,827 MPa)	378,000 psi (2,606 MPa)	285,000 psi (1,965 MPa)
Compressive Strength	11,360 psi (78 MPa)	12,890 psi (89 MPa)	10,000 psi (69 MPa)	10,900 psi (75 MPa)	10,200 psi (70 MPa)
Appearance, Mixed	Gray	Gray	Gray	Amber-Clear	Gray

Properties shown were determined at laboratory conditions.

### COVERAGE

CONCRETE BOND-108 LV: One Kg for 1.5m<sup>2</sup>

CONCRETE BOND-108 MV: One Kg for 1.00m<sup>2</sup>

CONCRETE BOND-108 GEL: One Kg for 1.25m<sup>2</sup>

CONCRETE BOND-108 (Primer) 0.5Kg for 1m<sup>2</sup>

Note: Coverage will vary with concrete surface texture, temperature, and the gradation of sand used for mortars. Coverage rates shown are approximate.

### DIRECTIONS FOR USE

**Surface Preparation:** Old concrete must be clean and well textured. All oil, dirt, debris, paint and unsound concrete must be removed. The surface should be prepared mechanically using equipment that will give a surface profile commensurate with the application. The final step in cleaning should be the complete removal of all residue with a vacuum cleaner or pressure washer.

**Bulk Mixing:** All materials should be in the proper temperature range of 60°F (16°C) to 90°F (32°C). Mix parts A and B (resin & hardener) using a drill and mixing prop. The epoxy must be well mixed to a uniform color with no streaking in order to ensure proper chemical reaction. If aggregate is to be added, the aggregate is added to the epoxy after the part A and part B have been premixed together. Place immediately.

**Application: (Priming, Bonding Or Sealing):** Use either Low Viscosity or Medium Viscosity formulations in these applications. Apply material by roller, brush, or squeegee in a uniform fashion. Do not allow the material to puddle. Extremely porous surfaces may require a second coat for proper ultimate performance.

**Priming & Bonding:** If using CONCRETE BOND-108 as a bonding agent for a cementitious topping, place the topping on the CONCRETE BOND-108 while the epoxy is still wet. If the epoxy has become "tacky" to the point where it is no longer a sticky liquid, a fresh coat of CONCRETE BOND-108 must be applied before the topping is placed.

# CONCRETE BOND - 108

**Sealing:** If a second coat of CONCRETE BOND-108 is to be placed on the concrete, the first coat should be slightly tacky (4 to 10 hours old) when the second coat is applied. A slip resistant surface can be created by broadcasting silica sand (20 to 50 mesh) into the coating and then backrolling to embed the sand.

**Repair Mortars:** Repair mortars can be made with these products by adding aggregate. Size, gradation and the amount of aggregate will be determined by the application. The surface should be primed with CONCRETE BOND-108 prior to application of the repair mortar. Mix the epoxy unit (Part A with Part B) prior to adding the aggregate. Trowel the mortar into place. If the surface is too rough, a topcoat of either DONCRETE BOND-108 or MV can be applied.

**Cartridge Epoxy Application Instructions:** Remove cap and divider plugs. Attach mixer tip and dispense epoxy with smooth, constant pressure. Discard epoxy until a uniform, streak-free color is achieved. Anchor installation: Insert the static mixer tip and fill hole from the bottom, slowly withdrawing the tip as the epoxy is dispensed until the hole is approximately half full. Insert the anchor with a slow, twisting motion to ensure complete epoxy contact with no air voids. Stabilize anchor until epoxy is cured.

## CLEAN-UP

Clean tools and equipment with solvent such as EUCO SOLVENT, xylene, or acetone before the epoxy hardens.

## PRECAUTIONS/LIMITATIONS

- This product may vary in color and may yellow and chalk in prolonged exposure to sunlight.
- Bring materials as close to 70°F (21°C) as possible. Store in room temperature environment 24 hours prior to use. Do not heat with open flame.
- Store indoors at 45°F to 110°F (7°C to 43°C).
- Epoxy components may cause skin irritation.
- Do not apply over freestanding water.
- Do not apply over hardened primer or old epoxy without proper surface preparation.
- Not recommended for use as a surface sealer over new concrete less than 30 days old.
- Not recommended for use when base concrete is at a temperature under 40°F (4°C).
- In all cases, consult the Material Safety Data Sheet before use.

## PACKAGING

CONCRETE BOND-108 epoxies are two part systems. Bulk packaged material is mixed at a 2 to 1 ratio by volume, Part A to Part B. 3 Kg/51 Kg /150 Kg.

## TECHNICAL COLLABORATION WITH



**Don Building Chemicals (India) Pvt. Ltd.**  
B-111-112, Santosh Complex, Vibhuti Khand,  
Gomti Nagar, Lucknow- 226010  
E-mail: [donbuildingchemicals@yahoo.com](mailto:donbuildingchemicals@yahoo.com)  
Website: [www.donbuildingchemical.com](http://www.donbuildingchemical.com)



**Doncrete USA Inc.**  
Governors Hwy 292, PA-8, Oil City  
PA-United States- 24601  
E-mail: [help@doncreteusa.com](mailto:help@doncreteusa.com)  
Website: [www.doncreteusa.com](http://www.doncreteusa.com)